DEKS

Technical Documents

1: Drawings DFE203RE

2: Flashings Technical Specifications

Follow Us On





PART NUMBER	DISPLAY NAME	MATERIAL
DFE103G	Dektite Premium #3 Gry (5-127mm/0.25-5")	EPDM/ALU
DFE103B	Dektite Premium #3 Blk (5-127mm/0.25-5")	EPDM/ALU
DFE103LGY	Dektite Premium #3 Light Gry (5-127mm/0.25-5")	EPDM/ALU
DFE103B_PP	Dektite Premium Blk (1/4-5") Bulk Pac	EPDM/ALU
DFE203RE	Dektite Premium #3 Red Sil (5-127mm/0.25-5")	SILICONE/ALU

DEKS Industries Pty. Ltd.
ABN 77 107 135 544

www.deks.com.au

TECHNICAL SPECIFICATION

PRODUCT RANGE: Dektite Roof Original and Premium Flashings

Working Temperature:

Black and Grey EPDM -50°C (-122°F) to 115°C (239°F) and Red Silicone -50°C (-122°F) to 200°C (392°F)

Property	Conditions	Method	Requirements As per IAPMO PS 64 -12	Result
Ultimate Elongation of Rubber	Die C	ASTM D412	Min. 210 % Elongation	Complies
Split Tear Strength of Rubber	Die C	ASTM D624	Min. 0.25 kN/m (EPDM), Min. 0.17 kN/m (Silicone)	Complies
Water Absorption of Rubber	48 hrs @ 158°F	ASTM D471	Max. change 5% by volume	Complies
Ozone Resistance of Rubber	72 hrs @ 104°F & 50 pphm Ozone	ASTM D1149 and D1171	No visible cracks	Complies
Low Temp. Brittleness of Rubber	Non-brittle 3 minutes @ -40°F, Method A	ASTM D2137	No brittleness	Complies
UV resistance of Rubber	UV: One cycle of 4 hrs @ 140°F. Condensation: 2000 hrs @ 122°F	ASTM G154	Max. 50% loss in Tensile Strength & Elongation	Complies
Rain Test for Flashing	Section 25	ANSI/UL 441	Pass	Complies
Temperature Test of Flashing	Section 19	ANSI/UL 441	Max. 90°F above the room temp.	Complies
Horizontal Burning Test / Flame spread of Flashing	Section 7	UL 94	Max. 75 mm/min	Complies

DEKS Industries Pty. Ltd.
ABN 77 107 135 544

www.deks.com.au

BAL Assessments Roof Flashings

Deks Industries Pty. Ltd. has tested its roof flashing for BAL (Bushfire Attack Level) to clause 20 of AS 1530.8.1 – 2007: "Methods for fire test on building materials, components and structures, Part 8.1 tests on elements of construction for buildings exposed to simulated bushfire attack – radiant heat and small flaming sources" and complies with it as per the table below.

All testing was completed by CSIRO Infrastructure Technologies.

BAL Rating	Models	Polymer	Use on min. 18° Roof Pitch for	CSIRO Report No.	Date of Issue
12.5	DC - Dektite Combo (no split) DFE – Dektite Premium DNL – Dektite Nu-Lead	EPDM EPDM EPDM	Metal Roofs Metal Roofs Tiled Roofs	EP1312912 EP1312912 EP1312992	Dec 2013 Dec 2013 Dec 2013
19	FFR – Fast Flash	MS Polymer	Tiled Roofs	EP159257	Dec 2015
29	DC - Dektite Combo (no split) DFE – Dektite Premium PFR - Perform	Silicone Silicone MS Polymer	Metal Roofs Metal Roofs Tiled Roofs	EP1312939 EP1312939 EP148152	Dec 2013 Dec 2013 Oct 2014